

METALTEC Cast Steel Shot Specifications

<p>CHEMICAL ANALYSIS (SAE J-2175)</p> <p>Carbon .10 - .15% Manganese 1.20 - 1.50% Silicon .10 - .25% Sulphur .035% MAX Phosphorous .035% MAX</p>	<p>DENSITY</p> <p>Cast steel shot shall not weigh less than 7 grams per cc nor contain more than 10% hollows. The method by which one determines density may be a displacement method or an actual count of the hollows in a mounted polished specimen.</p>	<p>BLENDS</p> <p>Special blends of two or more sizes of Metaltec cast steel shot are available at no extra charge. Pre-blended operating mixes for new equipment installations are also available at no extra charge.</p>																						
<p>BAINITE MICROSTRUCTURE</p> <p>Intermediate structure (Bainite), a mechanical mixture of Ferrite and Cementite particles. Random feather-like appearance (upper Bainite) and Accicular (lower Bainite) with little or no free carbon particles.</p>	<p>GENERAL APPEARANCE</p> <p>The cast steel shot shall be as nearly spherical as is commercially possible with a minimum of elongated or compound particles, tails, hollows, broken pieces, slag and dirt.</p>	<p>SAE SHOT SIZE (J-444)</p>	<p>APPROXIMATE PELLETS PER POUND</p>																					
<p>HARDNESS</p> <p>Ninety percent of the hardness checks performed on a representative sample shall fall within the range of Rockwell C 40 - 50. The hardness may be determined by any of the various methods applicable to small sections, such as a tukon tester with a Vickers indenter, at loads determined to provide a reliable conversion to Rockwell C.</p>	<p>PACKAGING</p> <p>Standard forms of packaging are: 2000-lb. drums, banded and palletized, and 50-lb. bags, boxed, banded, and palletized. Other special packaging available at extra cost.</p>	<table border="1"> <tbody> <tr><td>S780</td><td>17,000</td></tr> <tr><td>S660</td><td>20,000</td></tr> <tr><td>S550</td><td>32,000</td></tr> <tr><td>S460</td><td>55,000</td></tr> <tr><td>S390</td><td>93,000</td></tr> <tr><td>S330</td><td>153,000</td></tr> <tr><td>S280</td><td>250,000</td></tr> <tr><td>S230</td><td>420,000</td></tr> <tr><td>S170</td><td>1,200,000</td></tr> <tr><td>S110</td><td>3,400,000</td></tr> <tr><td>S70</td><td>17,000,000</td></tr> </tbody> </table>	S780	17,000	S660	20,000	S550	32,000	S460	55,000	S390	93,000	S330	153,000	S280	250,000	S230	420,000	S170	1,200,000	S110	3,400,000	S70	17,000,000
S780	17,000																							
S660	20,000																							
S550	32,000																							
S460	55,000																							
S390	93,000																							
S330	153,000																							
S280	250,000																							
S230	420,000																							
S170	1,200,000																							
S110	3,400,000																							
S70	17,000,000																							

**Test After Test, METALTEC Shot
Blasts the Competition Away!**

